

Test Report

Number: GZHH005279

Date: Mar 19, 2024

Sample Description:

One (1) group of submitted sample said to be :
Item Name : Vacuum Sealer Bags
Item No. : UVSBG-B11200-A
Reference Item No. : UVSBR-B332-A, UVSBR-B413-A
Country of Destination : US
Country of Origin : China
Date Sample Received : Feb 23, 2024 & Mar 11, 2024
Testing Period : Feb 23, 2024 ~ Mar 18, 2024

Tested sample



Tests conducted:

As requested by the applicant, refer to attached page(s) for details.

To be continued



Test Report

Number: GZHH005279

Conclusion:

Tested sample	Standard	Result
Tested component(s) of submitted sample(s)	U.S. F.D.A. Regulation 21 CFR Part 177.1520 Clauses (c)(2.1) on polyethylene	Pass
	U.S. F.D.A. Regulation 21 CFR Part 177.1500 Clause (b) (6.1) on nylon 6 resins	Pass
	Test Item Applicant's requirement for heavy metal content based on California Proposition 65	See test conducted
	Applicant's requirement on phthalates content Based on California Proposition 65	Pass
	Bisphenol –A Content	See test conducted

Authorized by:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch, Hardlines


Victor T.J. Wang
Assistant General Manager



Test Report

Number: GZHH005279

Tests Conducted

1 Test for F.D.A. Regulation on Polyethylene

As per the U.S. Food and Drug Administration 21 CFR Part 177.1520 Clauses (c)(2.1) and (d) with modification on density.

Test item	Result	Reporting Limit	Limit
	(3)		
Density (By sink-float method)	0.92	--	0.85 - 1.00
Maximum extractable fraction in n-hexane, %	ND	1.0	5.5 / 2.6
Maximum extractable fraction in xylene, %	3.8	1.0	11.3

ND = Not detected (less than reporting limit)

Tested Components: See component list in the last section of this report.

2 Test for F.D.A. Regulation on Nylon 6 Resins

As per the U.S. Food and Drug Administration 21 CFR Part 177.1500 Clauses (b) (6.1) and d(1-4).

Test item	Result	Reporting limit	limit
	(4)		
Specific gravity	1.146	--	1.135 to 1.165
Melting point, °F	415	--	392 to 446
Solubility in boiling 4.2N HCl	Complied	--	Dissolves in 1 hour
Maximum extractable fraction in water, %	0.22	0.10	1.0
Maximum extractable fraction in 95% ethyl alcohol, %	0.18	0.10	2.0
Maximum extractable fraction in ethyl acetate, %	ND	0.10	1.0
Maximum extractable fraction in benzene, %	ND	0.10	1.0

ND = Not detected(less than reporting limit)

Tested Components: See component list in the last section of this report.



Test Report

Number: GZHH005279

Tests Conducted

3 Total Lead (Pb) Content (CA 65 Requirement)

By microwave digestion and followed by Inductively Coupled Plasma (ICP) Spectrophotometric analysis.

Element	Result (ppm)	Reporting Limit (ppm)
	Tested Component	
	(1), (2)	
Lead (Pb)	ND	10

ppm = parts per million = mg/kg
ND = Not detected

Tested Component(s): See component list in the last section of this report

4 Phthalate Content (CA 65 Requirement)

By solvent extraction and Gas Chromatographic-Mass Spectrometric (GC-MS) analysis.

Test Item	CAS No.	Result (%)	Reporting limit (%)	Limit (%)
		Tested component		
		(1), (2)		
Dibutyl phthalate (DBP)	84-74-2	ND	0.01	0.1
Di-(2-ethyl hexyl) phthalate (DEHP)	117-81-7	ND	0.01	0.1
Benzyl butyl phthalate (BBP)	85-68-7	ND	0.01	0.1
Di-iso-nonyl phthalate (DINP)	28553-12-0	ND	0.01	0.1
Di-n-octyl phthalate(DNOP)	117-84-0	ND	0.01	0.1
Di-iso-decyl phthalate (DIDP)	26761-40-0	ND	0.01	0.1
Di-n-hexyl phthalate (DHEXP/DnHP)	84-75-3	ND	0.01	0.1
Di-cyclohexyl phthalate(DCHP)	84-61-7	ND	0.01	0.1
Diisobutyl phthalate (DIBP)	84-69-5	ND	0.01	0.1
Di-n-pentyl Phthalate (DPENP)	131-18-0	ND	0.01	0.1

ND = Not detected

Tested Component(s): See component list in the last section of this report



Test Report

Number: GZHH005279

Tests Conducted

5 Bisphenol-A Content

By solvent extraction and followed by Liquid Chromatographic / Tandem Mass Spectrometer (LC/MS/MS) analysis.

Test item	CAS No	Result (mg/kg)	Reporting limit (mg/kg)
		Tested component	
		(1)	
Bisphenol-A	80-05-7	ND	0.1

ND = Not detected(less than reporting limit)

Tested Components: See component list in the last section of this report

Components list:

- (1) Semi-transparent PE/PA6 plastic (bag).
- (2) White coating on plastic (surface of bag).
- (3) Light white PE plastic granule.
- (4) Light white PA6 plastic granule.




Test Report

Number: GZHH005279

Tests Conducted

Reference photo



End of report

The statements of conformity reported have considered the decision rule agreed, namely that Intertek have taken account of measurement uncertainty as calculated by Intertek, and applied according to ILAC-G8/09:2019 (Non-binary acceptance based on guard band **w = U**) except designation from the customer, regulation or test specification. This decision rule only applies to the numeric test results.

The sample(s) and sample information hereto are provided by the client who shall be solely responsible for the authenticity and integrity thereof. The results shown in this report relate only to the sample(s) tested. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. This report shall not be reproduced unless with prior written approval from Intertek Testing Services Shenzhen Limited, Guangzhou Branch. The testing data and result issued by this report are just for scientific research, teaching, internal quality control, product research and development etc. on reference only in the territory of the People's Republic of China.

